

A better environment inside and out.®

Safety & Security Window Films

Armorcoat® 7 Mil Clear


Performance results	1/8" (3mm)	1/4" (6mm)	1/8"+1/8" (3mm+3mm)
Solar energy			
% Transmittance	79	73	66
% Absorptance	13	19	21
% Reflectance	8	8	13
Visible light			
% Transmittance	89	87	80
% Reflectance exterior	9	9	16
% Reflectance interior	9	9	16
Emissivity	.90	.90	.90
Winter U-Factor (BTU hr/ft² °F)	1.07	1.09	.49
Shading coefficient	.95	.90	.85
Solar heat gain coefficient	.83	.78	.74
Solar selectivity index – luminous efficacy (VLT/SC)	.93	.97	.94
Light to solar heat gain factor (VLT/SHGC)	1.07	1.12	1.08
% Ultraviolet light blocked @ 300 to 380 nm	>99	>99	>99
% Total solar energy rejected	17	22	26
% Summer solar heat gain reduction	5	5	2
% Glare reduction	1	2	1

Physical properties nominal

Gauge	7.0 mil (175 micron)
Peel strength	>2,500 g/in (985 g/cm)
Tensile strength	30,000 lbs/in² (2,110 kg/cm²)
Break strength	210 lbs/in (38 kg/cm)
ASTM D4830 puncture test	118 lbs (52 kg)

Film performance

Performance results were generated from testing 1/8" (3mm) thick clear glass.



All performance results are based on the film installed on the inside surface of 1/8" (3mm), 1/4" (6mm), and 1/8"+1/8" (3mm+3mm) thick, clear glass.

Notes

- Solar Gard is a participating member of AIMCAL (the Association of Industrial Metallizers, Coaters and Laminators), IWFA, and EWFA. Performance results are calculated using NFRC methodology and LBNL Window 5.2 software, and are subject to variations within industry standards and only intended for estimating purposes.
- These test data contain only results arrived at after employing specific test procedures and standards. The included data do not constitute a recommendation for, endorsement of, or certification of the product or material tested. These data are provided for informational purposes only and are not to be considered part of the basic representation or warranty, expressed or implied, including the implied warranties of merchantability or fitness for a particular purpose, that its products will conform to these test data. Solar Gard's limited warranty should be carefully reviewed prior to purchasing any Solar Gard product. Extrapolation of data from the sample or samples relation to the batch or lot from which data were obtained may not correlate and should be interpreted accordingly with caution. Solar Gard shall not be responsible for variations in quality, composition, appearance, performance, or other feature of similar subject matter produced by persons or under conditions over which Solar Gard has no control.
- Performance results for summer solar heat gain reduction and glare reduction are calculated by comparing filmed glass to that of untreated glazing.



www.solargard.com/us

SK03147CLR 02/12

© Copyright 2012, Saint-Gobain Performance Plastics Corporation and/or its affiliates • All Rights Reserved • www.solargard.com

Please recycle

